

Technical datasheet No.: **1067.16**  
**Product:** VALMEX® print AIRTEX® FR  
**Article No.:** 7513 5300

<b>Type of coating and finish</b>			
Type of coating	TPU		
Burning behaviour	BS 5867 Part 2 Type B, California T 19, D.M. 26.06.84 (UNI 9177): CL. 1, NFPA 701 Test 2, DIN 4102: B1, EN 13501-1: B-s1-d0, BS 7837, NFP 92507: M1		
for Burning behaviour	always check validity of fire certificate, also check country-specific validity		
Total weight	260 g/m <sup>2</sup>	EN ISO 2286-2	
Tensile strength warp/weft	1200 / 1000 N/50 mm	EN ISO 1421/V1	
Tear strength warp/weft	130 / 80 N	DIN 53363	
Cold resistance	-30 °C	EN 1876-1	
High Temperature	+70 °C	PA 07.04 (intern)	
Crack resistance	no cracks	100000 x	DIN 53359 A
<b>Base fabric</b>			
Material	PES	DIN EN ISO 2076	
Weave	L 1/1	ISO 3572	
Remarks	no phthalates, PVC-free		

These indicated technical data are based on average results. Due to production procedures deviations up to -5% can occur. All technical data are in accordance with the present standard of knowledge and give product information without legal binding. All data apply to new products. Applications suggested do not release the customer to test material for its intended application.