

## MACal® Glass Decor 700

### PRODUCT DESCRIPTION

MACal Glass Decor 700 series are polymeric translucent vinyls coated with a long-life durable, highly cohesive acrylic pressure-sensitive adhesive. This is protected with a high quality plain or a bubble free (BF) liner.

**Face Material:** 80 µm matt polymeric translucent stabilized vinyl film, cadmium-free.

- **Plain:** High quality acrylic adhesive, very cohesive and extremely durable.
- **BF:** Micro-embossed, repositionable, clear acrylic adhesive.
- **Plain:** Highly stable 135 g/m<sup>2</sup> white kraft paper printed with MACtac backprinting.
- **Bubble Free (BF):** Highly stable 145 g/m<sup>2</sup> white micro-embossed PE coated paper with MACtac backprinting.

### TYPICAL USE

Decoration of windows and glass decor for an etched, frosted or sandblasted effect. Suitable for outdoor and indoor applications.

### PROCESSING

#### Screen process

MACal Glass Decor 700 series can be screen printed. Contact screen ink supplier for advice on suitable inks.

#### Computer cutting

Clean, quick, trouble-free cutting with most plotters. Adjustment of the cutting depth is important: if the cut is too deep this could result in the paper splitting and coming away with the adhesive when the vinyl is transferred to Application Tape. It is not recommended to plotter cut small letters with the BF version.

### APPLICATION METHOD

Application of pre-spaced letters, logos and decals made from MACal Glass Decor 700 is made easier using MACtransfer Application Tape. For an uniform appearance, GlassDecor 700 plain is applied by the wet method whereas the BF version should be applied dry.

Due to its unique finish, variances in appearance can be visible when the material is oriented in different directions. When utilizing MACal Glass Decor 700, always keep the application direction of the film consistent with the orientation of the film when cut from the roll and applied to the glass.

These films can be removed without leaving adhesive residue on most glass surfaces.

### SHELF LIFE

2 years when stored at 15 to 25°C and ± 50 % relative humidity (in the original packaging).

### PHYSICAL PROPERTIES (TYPICAL VALUES)

#### Average Values Test Method

| Thickness                | Plain | BF  |         |
|--------------------------|-------|-----|---------|
| Film + Adhesive (micron) | 115   | 110 | ISO 534 |

#### Face Material data, 23°C

|                           |       |               |
|---------------------------|-------|---------------|
| Tensile Strength (N/15mm) | > 28  | DIN ISO 527-3 |
| Elongation at Break (%)   | > 150 | DIN ISO 527-3 |

#### Adhesive data, 23°C (N/25 mm)

Peel adhesion 180° on stainless steel

|                     | Plain | BF |      |
|---------------------|-------|----|------|
| - 20 min. residence | 14    | 16 | FTM1 |
| - 24 hour residence | 17    | 17 | FTM1 |
| - 1 week residence  | 19    | 19 | FTM1 |

#### Dimensional stability

|   |            |       |
|---|------------|-------|
| Shrinkage (1 week at 70°C applied on Aluminium) | Max 0.3 mm | FTM14 |
|---|------------|-------|

#### Temperature ranges

|                                       |                |
|---------------------------------------|----------------|
| Minimum application temperature (°C): | +10°C          |
| Service temperature range (°C):       | -40°C to +90°C |

#### Flammability

|                             |         |            |
|-----------------------------|---------|------------|
| Sample mounted on aluminium | B-s1,d0 | EN 13501-1 |
|-----------------------------|---------|------------|

### Solvent and chemical resistance

|                     |   |
|---------------------|---|
| Resistance to most: | Resistant to most oils and grease, fuel, aliphatic solvents, weak acids, salts and alkalis. |
|---------------------|---|

### EXPECTED DURABILITY

#### Central Europe Zone 1

The expected vertical outdoor durability of the unprocessed product in central Europe (Zone 1) is up to 5 years. This information is based on successful real life experience and artificial aging according to ISO4892-2.

*Note : Exposure to severe temperatures and ultraviolet light, as well as conditions in southern European countries, and also in tropical, sub-tropical or desert regions, will cause a more rapid deterioration. This also applies to polluted areas, high altitude, horizontal and south-facing exposure.*

#### DISCLAIMER

For more information on the durability and exposure please visit the “Mactac Technical Bulletin TB 7.5 Outdoor Durability of Mactac Graphics - Self-adhesive films” on the [www.https://www.mactacgraphics.eu](https://www.mactacgraphics.eu) website.

Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>. Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.

#### Contact

Email: [mactac.europe@mactac.eu](mailto:mactac.europe@mactac.eu)

Website: [www.mactacgraphics.eu](http://www.mactacgraphics.eu)

